
HC250E硅胶导热

HC250ESilicone thermal pad

TDS



HC250E is a universal thermal gasket with no special heat dissipation requirements for hardness. Its softness can meet most pressure assembly requirements, showing a small thermal resistance, and at the same time eliminate the air between components and circuit boards, and fully fill all kinds of rough surfaces.The product comes with stickiness.The default is no substrate structure, can be customized to have the substrate structure, such as silicon backing adhesive /3M adhesive/glass fiber and other processes to meet the special requirements.

The characteristics of


• thermal conductivity = 2.5w /m.k

• high adhesion, ultra-low hardness, suitable for low fastening pressure


• fire protection meets V0 and environmental protection meets ROHS requirements

• good resilience

The relationship between stress and strain



The relationship between thickness and thermal resistance



Physical property parameters table		
Product performance	Test values	test method
Main components of materials	Silica gel + thermal ceramic powder	—
color	gray	Visual
Thickness range (mm)	0.3 - 10	ASTM D374
Density (g/cc)	1.9	ASTM D792
Hardness (ShoreC) thickness: 0. 3mm	20	ASTM D2240
Hardness (Shore00) thickness ≤3mm	20	ASTM D2240
Applicable temperature (℃)	-40 ~200	EN344
Insulation breakdown voltage (Vac)	>4000	ASTM D149
Dielectric constant (1MHz)	5.5	ASTM D150
Volume resistivity (Ohm-meter)	$8.3*10^{12}$	ASTM D257
Low molecular siloxane d3-d12 (PPM)	< 300	GB/T27843-2011
Fire rating	94V-0	U.L
Thermal conductivity (W/ m-k)	2.5	ASTM D5470
Recommended amount of compression	30%	—

Thickness tolerance ≤ 10% of product thickness

Typical applications

•Communications industry

•Computer and peripheral

•Power converter

•Between a semiconductor or magnetic body and a radiator

•Heat transfer frames, chassis or other heat transfer areas are required

Available specifications: sheet, die - cutting

Standard thickness mm: 0.3, 0.5, 1.0, 1.5, 2.0, 2.5, 3.0 other thickness needs to be customized

Standard length and width mm: 200*400, 300*400 other sizes need to be customized

Storage conditions: temperature 10-30℃, humidity: 70%

Description:

This product can be mixed with glass fiber (FG), single back silicon tape (SP), one side with viscosity and one side without viscosity (DC).Please refer to the MSDS report for the safety data of the product. The data in this paper are obtained under laboratory conditions. Due to the differences in the use conditions, users need to refer to these data and use conditions for analysis and test.The company does not guarantee the sale of the product or the use of the company's products under specific conditions, and is not liable for any direct, indirect or accidental loss.
If you have any problem, you can contact the technical service department of the company.

Address: Building B, pengwuZhiquan high-tech Park, Dongkeng town, Dongguan City

Web：http://www.kuayuetech.com http://coyomo.en.alibaba.com

Tel:0769 - - 83699986 E.mail: acc001@szkuayue.com



